

General features for MPPS Series battery (OPzS)

- * Tubular positive plate;separator with the combined application of porous rubber and porous PVC,separator is with a high porosity & good corrosion resistance.
- * Computer designed lead, calcium tin alloy grid for high power density.
- * Long service life, float or cyclic applications:designed floating life is 20years at 25°C;Designed cycle life more than 1200 cycles at 80% DOD at 25°C/77 F.
- * Acid-proof bolt:
It is of a special shape of funnel having the function of filtering acid smog and retarding flame,it can measure the density and temperature of electrolyte.
- * Ensuring sufficient electrolyte for battery discharge.
- * Battery container is transparent ,easy checks electrolyte.



Maxton Power Tech Co.,Ltd
www.maxtonpower.com
info@maxtonpower.com

MPPS2-3000 (2V3000Ah)


Specifications

Nominal Voltage		2 V
Rated capacity (10 hour rate)		3000 Ah
Dimensions (±3mm)	Total Height (Include terminal)	826mm (32.5inches)
	Height	771mm (30.4inches)
	Length	576mm (22.7 inches)
	Width	212mm (8.4inches)
Approx Weight (±5%)	Without electrolyte	147.0Kg (324.1lbs)
	With Electrolyte	210.0Kg (463.1lbs)
	Electrolyte weight (d=1.25kg/l)	Approx 63.0Kg (138.9lbs)

Battery picture and construction



Connection method for reference:




Battery Construction


Component	Positive plate	Negative plate	Container	Cover
Raw material	Lead dioxide	Lead	SAN transparent	ABS
Component	Electrolyte	Separator	Safety valve	Terminal
Raw material	Dilute sulfuric acid	PVC	Porous rubber	Copper

Outer dimension and terminal

Terminal:TP



Outer dimensions(±3mm) Unit:mm



Characteristics

Capacity 25°C(77°F)	10 hour rate(300A,1.8V) 3 hour rate(771A,1.75V) 1 hour rate(1680 A,1.60V)	3000Ah 2313Ah 1680Ah
Internal Resistance	Full charged battery at 25°C(77°F)	Approx 0.20 mΩ
Capacity affected by Temperature (10hour rate)	40°C (104°F) 25°C (77°F) 0°C (32°F) -15°C (5°F)	102% 100% 85% 65%
Remaining capacity Self-Discharge At 25°C(77°F)	Capacity after 3 month storage Capacity after 6 month storage	≥ 88% ≥ 76%
Terminal type	TP (copper)	
Max. Discharge current 25°C/(77°F)	15000A (5Seconds)	
Nominal operating temperature	25°C ±5°C(77°F ±9°F)	
Operating Temperature Range	Discharge Charge Storage	-15°C ~50°C (5°F ~122°F) -10°C ~50°C (14°F ~122°F) -20°C ~50°C (-4°F ~122°F)
Charge methods (constant Voltage) At 25°C(77°F)	Cycle use	Initial Charging Current less than 750A Voltage 2.35-2.45V Temperature compensation:-5mV/°C
	Standby use	Voltage 2.25-2.30V Temperature compensation:-3mV/°C

Constant current discharge (25°C , 77 °F)

Unit:A

Constant power discharge (25°C , 77 °F)

Unit:watts


Constant Current(Amp) and Constant Power(Watt) Discharge Table at 25°C(77°F)

Time	30min	1h	2h	3h	5h	6h	8h	10h	20h	24h	48h	100h
1.65V	A 2140.2	1659.5	1090.0	819.1	559.0	452.2	384.0	317.0	171.5	143.5	76.8	37.8
	W 4490	3391	2449	1638	1099	1018	869	628	326.4	293.8	194.4	100.8
1.70V	A 2053.4	1590.6	1065.0	796.6	547.0	443.8	376.5	312.0	169.4	143.0	76.3	37.8
	W 4167	3297	2426	1631	1080	991	854	619	323.0	290.9	193.9	100.3
1.75V	A 1900.8	1510.1	1005.0	771.0	533.0	433.7	370.5	307.0	166.7	142.6	75.4	37.4
	W 3726	3193	2410	1605	1066	968	840	614	319.7	288.0	193.4	99.8
1.80V	A 1690.0	1390.1	950.0	732.0	510.0	423.5	353.5	300.0	162.0	142.1	74.9	37.2
	W 3062	2891	2355	1552	1048	960	810	599	316.8	285.1	193.0	99.4
1.85V	A 1350.0	1190.0	870.0	670.0	479.0	403.5	333.0	283.5	153.0	135.4	74.4	37.1
	W 2253	2543	2149	1435	1012	945	775	585	312.0	272.2	192.5	98.9


(Above characteristics data are average values obtained within three charge/discharge cycles,not the minimum values.)

OPzS Battery (Tubular plate technology) Flooded Lead Acid Rechargeable Battery


Discharge characteristics (25°C, 77°F)




Charge characteristics (25°C, 77°F)




Life characteristics of Cyclic Use (25°C, 77°F)




Effect of Temperature on capacity




Self-discharge characteristics (with full charging)




Initial charging characteristics



Relationships for open voltage and remained capacity (for reference)



Relationship for service life and temperature



Effect of discharge rate on capacity

